






| TARALAY PREMIUM METALLICA COMPACT | | | |
|---|-----------------|------------------|--|
| DESCRIPTION | | | |
| Total thickness | EN 428 | mm | 2 |
| Thickness of wearlayer | EN 429 | mm | ≥ 1.00 |
| Weight | EN 430 | g/m ² | 2620 |
| Width of sheet | EN 426 | cm | 200 |
| Length of sheet | EN 426 | lm | 20 |
| CLASSIFICATION | | | |
| Norm / Product specification | | | EN 649 |
| European classification | EN 685 | class | 34 - 43 |
| Classification K | - | class | |
| Fire rating | EN 13 501-1 | class | B _{fl} s1 |
| Static electrical propensity | EN 1815 | kV | < 2 |
| PERFORMANCE | | | |
| Wear resistance | EN 660.1 | mm | ≤ 0.08 |
| Wear group | EN 649 | - | T |
| Dimensional stability | EN 434 | % | ≤ 0.40 |
| Residual indentation | EN 433 | mm | ≤ 0.10 |
| Thermal conductivity | EN 12 524 | W/(m.K) | 0,25 |
| Colour fastness | EN 20 105 - B02 | degree | ≥ 6 |
| Chemical products resistance | EN 423 | - | OK |
| Anti-bacterial and fungicidal treatment | - | - | |
| Surface treatment | - | - | Protecsol® |
| MARQUAGE CE | | | |
|  | EN 14041 | |     |